



WAKEFIELD

INSTRUMENT SERVICES

Americas • Europe • Africa • Asia • Australia

Test Location:	JSC "Tajikistan-WIS"	Recipient / Customer:	FARNICO TAJIKISTAN LLC
C/I Number:		Origin:	Tajikistan
C/I Report Number:	D/218-2	Station (As advised):	Crop 2022
Date:	2022.12.02.	Variety (As advised):	Upland Cotton
Lot number	263-011	Samples drawn by Costomer	10 Samples

Bale ID	Amt	SCI	Grade	Moist	Mic	Mat	UHML	UI	SFI	Str	Elg	Rd	+b	C Grade	Tr Cnt	Tr Area	Tr ID
				[dry%]			[in]	[%]	[0.5in]	[g/tex]	[%]			[Upland]		[%]	LeafGrd
X1	551	122		8.6	4.54	0.86	1.142	82.1	8.45	27.9	7.0	76.1	9.4	31-3	37.0	0.78	4
012	603	131		8.2	4.44	0.86	1.090	82.9	8.02	29.8	7.2	77.5	8.7	31-1	33.0	0.89	4
018	599	130		8.3	4.35	0.86	1.135	82.2	7.37	30.1	7.1	76.2	9.0	31-3	47.0	1.14	4
023	532	129		8.4	4.41	0.86	1.133	82.1	8.44	30.1	7.4	75.7	8.8	31-3	39.0	0.94	4
041	545	130		8.7	4.54	0.86	1.120	82.9	7.56	29.5	6.9	77.3	8.9	31-1	29.0	0.50	3
054	617	125		8.6	4.69	0.87	1.126	82.6	9.17	29.1	6.7	75.6	8.4	31-2	48.0	0.88	4
064	511	132		8.1	4.56	0.86	1.097	84.2	8.16	28.6	7.3	76.2	8.9	31-3	36.0	0.59	3
067	513	130		8.8	4.41	0.86	1.132	82.3	8.85	30.2	7.0	75.5	8.7	31-2	44.0	1.37	3
074	490	131		8.9	4.52	0.86	1.102	83.6	8.01	29.1	7.0	77.2	8.5	31-1	32.0	0.66	3
088	532	135		7.9	4.63	0.86	1.145	83.4	7.34	30.4	7.9	77.2	9.0	31-3	42.0	0.91	4
n	10																
Max	617	135		8.9	4.69	0.87	1.145	84.2	9.17	30.4	7.9	77.5	9.4	31-3	48.0	1.37	4
Min	490	122		7.9	4.35	0.86	1.090	82.1	7.34	27.9	6.7	75.5	8.4	31-1	29.0	0.50	3
Average	549	129		8.4	4.51	0.86	1.122	82.8	8.14	29.5	7.2	76.4	8.8	31-3	38.7	0.87	4
Std.Dev.	41	3		0.3	0.10	0.00	0.018	0.7	0.58	0.8	0.3	0.7	0.3		0.0	0.24	
CV%	7	3		3.6	2.24	0.37	1.640	0.8	7.13	2.6	4.7	0.9	3.1		0.0	28.17	
Q99% +/-	36	3		0.3	0.09	0.00	0.016	0.6	0.51	0.7	0.3	0.6	0.2		0.0	0.21	

Remarks:

1. **Note: Samples were NOT drawn by WIS.**
2. Samples tested will be stored for 3 months only, after which they will be disposed of at Wakefield's discretion, unless otherwise instructed.
3. All comments and queries of results shown in this report should be made in writing within thirty days of the issue of this report.
4. The report shall not be used for Litigation or Publicity.
5. If requested by customer WIS may its own personal to draw the customer's cost.

This report reflects only the results of test carried out on samples submitted to us and tested on S.I.T.C. instruments on the date(s) mentioned and at the location shown, does not certify to any description given and is issued without prejudice. In all instance only the English version of this report is to be considered definitive and correct.

Test and lab conditions

The tests were made under the conditions laid down in the Guideline for Instrument Testing of Cotton, published by; ICAC Task Force on Commercial Standardization of Instrument Testing of Cotton (CSITC) and ITMF International Committee on Cotton Testing Methods (ICCTM)

- 1) HVI Calibration Cottons used for calibration.
- 2) A laboratory temperature of 21° ± 1° C
- 3) A relative humidity of 65 ± 2%
- 4) A sample moisture level between 6.75% and 8.25%
- 5) Standard instrument tolerance applicable

ЧСП "Тоҷикистон-ВИС (Санчиши мустақили пахта)"
 JSC "Tajikistan-WIS (Independent inspection of cotton)"

Чумхури Тоҷикистон
 ш. Душанбе
 қ. Каҳоров 111
 Ph +992 37 260 68 40
 Fx +992 37 260 68 58
 Em kamol_taj-wis@mail.ru

Kahorova str.111
 Dushanbe
 Republik Tajikistan
 Ph +992 37 260 68 40
 Fx +992 37 260 68 58
 Em kamol_taj-wis@mail.ru

