



Test Location:	JSC "Tajikistan-WIS"	Recipient / Customer:	FARNICO TAJIKISTAN LLC
C/I Number:		Origin:	Tajikistan
C/I Report Number:	D/218-3	Station (As advised):	Crop 2022
Date:	2022.12.02.	Variety (As advised):	Upland Cotton
Lot number	263-013	Samples drawn by Costomer	5 Samples

Bale ID	Amt	SCI	Grade	Moist	Mic	Mat	UHML	UI	SFI	Str	Elg	Rd	+b	C Grade	Tr Cnt	Tr Area	Tr ID
				[dry%]			[in]	[%]	[0.5in]	[g/tex]	[%]			[Upland]		[%]	LeafGrd
X1	570	144		8.7	4.51	0.85	1.177	83.5	8.08	32.2	8.5	78.8	8.4	31-1	33.0	0.24	3
008	679	133		7.8	4.54	0.86	1.157	83.4	7.73	29.4	7.4	76.0	8.6	31-2	43.0	0.85	4
012	578	144		8.6	4.54	0.86	1.136	84.4	7.88	31.5	8.1	78.6	8.5	21-2	39.0	0.61	3
018	578	128		7.8	4.60	0.86	1.113	82.4	8.73	29.7	8.0	78.8	8.8	21-2	29.0	0.39	3
026	592	127		8.6	4.48	0.86	1.085	82.8	8.82	29.2	7.4	76.8	8.9	31-1	43.0	0.61	4
n	5																
Max	679	144		8.7	4.60	0.86	1.177	84.4	8.82	32.2	8.5	78.8	8.9	31-2	43.0	0.85	4
Min	570	127		7.8	4.48	0.85	1.085	82.4	7.73	29.2	7.4	76.0	8.4	21-2	29.0	0.24	3
Average	599	135		8.3	4.53	0.86	1.134	83.3	8.25	30.4	7.9	77.8	8.6	31-1	37.4	0.54	3
Std.Dev.	40	8		0.4	0.04	0.00	0.033	0.7	0.44	1.2	0.4	1.2	0.2		0.0	0.21	
CV%	7	6		4.8	0.86	0.29	2.866	0.8	5.39	4.0	5.6	1.5	1.9		0.1	38.82	
Q99% +/-	61	11		0.6	0.06	0.00	0.049	1.0	0.67	1.8	0.7	1.8	0.2		0.0	0.32	

Remarks:

- Note: Samples were NOT drawn by WIS.**
- Samples tested will be stored for 3 months only, after which they will be disposed of at Wakefield's discretion, unless otherwise instructed.
- All comments and queries of results shown in this report should be made in writing within thirty days of the issue of this report.
- The report shall not be used for Litigation or Publicity.
- If requested by customer WIS may its own personal to draw the customer's cost.

This report reflects only the results of test carried out on samples submitted to us and tested on S.I.T.C. instruments on the date(s) mentioned and at the location shown, does not certify to any description given and is issued without prejudice. In all instance only the English version of this report is to be considered definitive and correct.

Test and lab conditions

The tests were made under the conditions laid down in the Guideline for Instrument Testing of Cotton, published by: ICAC Task Force on Commercial Standardization of Instrument Testing of Cotton (CSITC) and ITMF International Committee on Cotton Testing Methods (ICCTM)

- HVI Calibration Cottons used for calibration.
- A laboratory temperature of 21° ± 1° C
- A relative humidity of 65 ± 2%
- A sample moisture level between 6.75% and 8.25%
- Standard instrument tolerance applicable

ЧСП "Тоҷикистон-ВИС (Санчиши мустақили пахта)"
JSC "Tajikistan-WIS (Independent inspection of cotton)"

Чумхурии Тоҷикистон
ш. Душанбе
к. Каҳорова 111
Ph +992 37 260 68 40
Fx +992 37 260 68 58
Em kamol_taj-wis@mail.ru

Kahorova str.111
Dushanbe
Republik Tajikistan
Ph +992 37 260 68 40
Fx +992 37 260 68 58
Em kamol_taj-wis@mail.ru

